

## DIAMETERS

- 4.00in/102mm
- 5.00in/127mm

# MD-500™

Designed for large volume water supply where light weight and low drag coefficient are critical

- » Unique Mertex® lining yields an extremely low friction loss, for maximum flow and superior adhesion for long life
- » Premium all synthetic double jacket
- » Choice of Threaded or Storz lightweight couplings
- » Standard with Permatek HP™ treatment against abrasion, moisture pick up and mildew
- » Resistant to most chemicals, petrol products, ozone and U.V. exposure, hydrolysis, and rot and mildew
- » Remains flexible to -65° F (-55° C)

clear
tan
black
orange
red
blue
green
yellow
purple

Hose Spec.	Trade Size	Bowl Size	Weight UN-COUPLED 50' (15.2m)	Coil Diameter 50' (15.2m)	Service Pressure	Proof Pressure	Burst Pressure
650	In. mm	In. mm	Lbs Kg	In. Cm.	PSI kPa	PSI kPa	PSI kPa
650	4.00 102	4 3/8 111	34.5 15.7	16.0 40.6	250 1 725	500 3 450	750 5 175
651	5.00 127	5 3/8 137	43.5 19.8	17.0 43.2	250 1 725	500 3 450	750 5 175



**MERCEDES  
TEXTILES LIMITED**

5838 Cypihot  
Saint Laurent, QC  
Canada, H4S 1Y5

PHONE 514.335.4337  
PHONE 877.937.9660  
FAX 514.335.9633

[mercedestextiles.com](http://mercedestextiles.com)  
[sales@mercedestextiles.com](mailto:sales@mercedestextiles.com)



# HOW TO SPECIFY

## MD-500™

**THE HOSE SHALL BE DOUBLE JACKET  
WITH A SERVICE TEST PRESSURE OF  
250 PSI / 1725 KPA.**

---

### JACKETS

The inner jacket shall be made with high tenacity filament polyester yarn in both the warp and weft directions, to provide maximum strength.

The outer jacket shall be made with virgin spun polyester warp yarn and a filament polyester weft yarn. The outer jacket shall have a minimum of 10 filament polyester weft yarn picks per inch (394 per Meter) and shall be impregnated in one of the standard NFPA colors with high performance polymeric dispersion.

### LINING

The lining (waterway) must be made from polyurethane and must be applied using a fused process that welds the polyurethane directly to the textile while the hose is being woven, without the use of adhesives or hot melt. The fused lining process must create a virtually inseparable unit without the use of adhesives, yielding an extremely low friction (pressure) loss by filling in the corrugations of the weave, creating an ultra thin and smooth waterway. Fire hose made using adhesives of any type do not meet this specification. The lining shall be approved for use with potable water.

### ADHESION

The adhesion shall be such that the rate of separation of a 1 ½" / 38mm strip of polyurethane, transversely cut, shall not be greater than 1/4" / 6mm per minute under a weight of 12 lbs / 5.5 kg.

### COLD TEMPERATURE FLEXIBILITY

The hose must remain flexible to -65°F (-55°C).

### SERVICE, TEST, BURST PRESSURES

Minimum service, test and burst pressures shall be as detailed in the specification table on the previous page.

### KINK TEST

A full length will withstand a hydrostatic pressure of 600 psi / 4140 kPa while kinked.

### WEIGHT

Each length of fire hose shall not weigh more than indicated in the specification table.

### COUPLING SPECIFICATIONS

Couplings shall be in conformance with the current NFPA standard and made of extruded aluminum, hard coated a minimum of .002" thick. They shall be manufactured in North America and permanently labeled with country of origin. They shall be available in threaded expansion ring type or Storz fittings.

### MANUFACTURE

Both hose and couplings must be manufactured in North America. Couplings must be USMCA compliant.