


DIAMETERS

- 1.50in/38mm
- 1.75in/45 mm
- 2.50in/64 mm
- 3.00in/76mm

MTSS-800™

Designed for the cost conscious fire service

- » Unique Mertex® lining
- » Premium all synthetic double jacket
- » Available with the Identify® recessed area for color coding, bar coding and/or identification markings
- » Available with Permatek HP™ treatment against abrasion, moisture pick up and mildew
- » Resistant to most chemicals, petrol products, ozone and U.V. exposure, hydrolysis, rot and mildew
- » Will remain flexible to -40° F (-40° C)
- » All sizes and colors are tested according to the procedures specified in "2020 UL 19 radiant heat test"
- » Meets or exceeds all performance requirements of NFPA 1960 (1961), Underwriters Laboratories and Factory Mutual



Hose Spec.	Trade Size		Bowl Size		Weight Un-coiled 50' (15.2m)		Coil Diameter 50' (15.2m)		Service Pressure		Proof Pressure		Burst Pressure	
	In.	mm	In.	mm	Lbs	Kg	In.	Cm.	PSI	kPa	PSI	kPa	PSI	kPa
429	1.50	38	1 13/16	46	11.0	5.0	15.5	39.4	400	2 755	800	5 515	1 200	8 275
430	1.75	44	2	51	13.0	5.9	15.5	39.4	400	2 755	800	5 515	1 200	8 275
432	2.50	64	2 7/8	73	20.0	9.1	16.5	41.9	400	2 755	800	5 515	1 200	8 275
433	3.00	76	3 5/16	84	26.0	11.8	18.0	45.7	400	2 755	800	5 515	1 200	8 275



**MERCEDES
TEXTILES LIMITED**
Innovation delivered.™

5838 Cypihot
Saint Laurent, QC
Canada, H4S 1Y5

PHONE 514.335.4337
PHONE 877.937.9660
FAX 514.335.9633

mercedestextiles.com
sales@mercedestextiles.com

HOW TO SPECIFY

MTSS-800™

THE HOSE SHALL BE DOUBLE JACKET WITH A SERVICE TEST PRESSURE OF 400 PSI / 2750 KPA.

.....

JACKETS

The inner shall be made with virgin spun polyester warp yarn.

The outer jacket shall be made with virgin spun polyester warp yarn and shall have a minimum of 10 filament polyester weft yarn picks per inch (394 per Meter). When requested it shall be impregnated in one of the standard NFPA colors with high performance polymeric dispersion.

LINING

The lining (waterway) must be made from polyurethane and must be applied using a fused process that welds the polyurethane directly to the textile while the hose is being woven, without the use of adhesives or hot melt. The fused lining process must create a virtually inseparable unit without the use of adhesives, yielding an extremely low friction (pressure) loss by filling in the corrugations of the weave, creating an ultra thin and smooth waterway. Fire hose made using adhesives of any type do not meet this specification. The lining shall be approved for use with potable water.

ADHESION

The adhesion shall be such that the rate of separation of a 1 1/2" / 38mm strip of polyurethane, transversely cut, shall not be greater than 1/4" / 6mm per minute under a weight of 12 lbs / 5.5 kg.

COLD TEMPERATURE FLEXIBILITY

The hose must remain flexible to -40°F (-40°C).

FLOW AND FRICTION LOSS

1 3/4 inch (44mm) diameter, 100 US GPM (379 LPM), shall not exceed 10.0 PSI (69 KPa) loss per 100 feet (30.5 M).

SERVICE, TEST, BURST PRESSURES

Minimum service, test and burst pressures shall be as detailed in the specification table on the previous page.

KINK TEST

A full length will withstand a hydrostatic pressure of 600 psi / 4140 kPa while kinked.

WEIGHT

Each length of fire hose shall not weigh more than indicated in the specification table.

COUPLING SPECIFICATIONS

The Hard Coat anodized couplings shall be manufactured in North America, and permanently labeled with country of origin. They shall be expansion ring type. The male coupling and female swivel nut must both have a recessed area to facilitate color and bar coding and/or identification markings.

STANDARDS

The hose must meet or exceed all performance requirements of NFPA 1960 (1961), Underwriters Laboratories and Factory Mutual.

The hose must also be tested in accordance with the procedures specified in "2020 UL 19 radiant heat test".

MANUFACTURE

Both hose and couplings must be manufactured in North America. Couplings must be USMCA compliant.